

# PEARL GRADING REPORT

No. EG00003129



## CONCLUSION

**Akoya cultured pearl**

DESCRIPTION OF ARTICLE(S)

**Strand 9.0-9.5mm**

DEGREE OF PROCESSING\*

( \* ) ENHANCEMENT ( ) TREATMENT

**Hanadama quality pearl**

Nacre thickness 0.80mm

Quality Items	I	II	III	IV	V
Nacre thickness	*				
	Thickly coated	Fairly thickly coated	Ordinary~ somewhat thinly coated	Thinly coated	Nearly no nacre
Shape	*				
	Round~ near round	Near round including slight off shape	Off shape	Baroque	Extreme baroque
Luster	*				
	Strong luster	Fairly strong luster	Ordinary luster	Weak luster	Almost no luster
Flaw	*				
	Flawless~ tiny flaw	Tiny~ medium flaw	Medium flaw	Heavy flaw	Very heavy flaw
Finishing & matching	*				
	Excellent	Good	Acceptable	Poor	Very poor

In conformity with Export inspect of former National Pearl Cultivation Law

## Main inspection methods

Ultrasonography    UV/visible spectroscopy    Naked eye inspection  
 Inspection by light penetration    Microscopy    Other inspections

株式会社 真珠総合研究所

PEARL INSTITUTE Co., Ltd.

4-14-8, Taito, Taito-ku, Tokyo, 110-0016 JAPAN

